


Desired Material Attributes

Lens Material	Lightweight = Low Density (g/cm3)	THIN - High Refractive Index	Good Optical Quality = High Abbe Number	Safety = High Impact Resistance
Glass	2.2 - 2.54	1.45 - 1.7	64 - 67 (best)	Low, unless thick (heavy)
PMMA (Acrylic)	1.19	1.491	57	Marginal
CR-39® or Hard Resin	1.32	1.498	58	Marginal
Polycarbonate	1.2	1.586	30- 34.5	High
Mid-index Plastics	1.2	1.52 - 1.56	35 - 43	Marginal
High Index Plastics	1.3 - 1.4	1.59 - 1.67 (best)	32-41	Marginal
Inventors' Modified Polymeric Material	1.11 (best)	1.53	45.5	High

Table 1

United States Patent & Trademark Office
Office of Initial Patent Examination -- Scanning Division



Application deficiencies found during scanning:

☒ Page(s) 8 of 1 Drawing were not present
for scanning. (Document title)

☒ Page(s) _____ of Assignment were not present
for scanning. (Document title)

☐ *Scanned copy is best available.*